ISSN Print: 2394-7500
ISSN Online: 2394-5869
Impact Factor (RJIF): 8.4
IJAR 2023; 9(7): 379-384
www.allresearchjournal.com
Received: 28-05-2023
Accepted: 02-07-2023

Dr. Manoj Kumar Sinha
Associate Professor,
Department of Physics,
Butwal Multiple Campus,
Butwal, Nepal

Corresponding Author:
Dr. Manoj Kumar Sinha
Associate professor,
Department of Physics,
Butwal Multiple Campus,
Butwal, Nepal

Advances in hybrid solar cells: A review of organic-inorganic photovoltaic technologies

Dr. Manoj Kumar Sinha

Abstract
Hybrid solar cells represent a promising alternative to traditional silicon-based photovoltaic systems due to their cost efficiency, tunability, and ease of fabrication. These devices merge the unique properties of organic materials—such as flexibility and molecular designability—with the high absorption coefficients of inorganic nanoparticles. This review presents a comprehensive overview of the various hybrid solar cell architectures, including dye-sensitized solar cells (DSSCs), nanoparticle-sensitized solar cells, extremely thin absorber (ETA) cells, and bulk heterojunction (BHJ) devices. Key advancements in material synthesis, device architecture, and performance metrics are discussed, providing insights into the current challenges and future research directions.

Keywords: Bulk heterojunction solar cells, polymer/fullerene blend morphology, P_3HT solar cells, electron microscope images of bhj solar cells

1. Introduction
Photovoltaic technologies have undergone significant advancements in recent decades, with hybrid solar cells emerging as a cost-effective and scalable alternative to traditional silicon-based devices. Hybrid solar cells combine organic and inorganic materials to exploit the strengths of both material classes, including low cost, tunable optical properties, and the ability to manufacture devices using solution processes.

1.1. Electrical Characteristics of Solar Cells
The performance of solar cells is characterized by several key metrics, including the open circuit voltage V_{OC}, short-circuit current I_{SC}, fill factor (FF), and power conversion efficiency (PCE). The I-V curve of a typical solar cell shows these characteristics, where P_{max} is determined by maximizing the product of current and voltage (Figure 1).

$$\eta = \frac{V_{OC} \times I_{SC} \times FF}{P_{in}}$$

Where P_{in} is the incident light power.

2. Hybrid Solar Cells
Hybrid solar cells are designed by integrating organic polymers with inorganic nanoparticles. These systems are advantageous due to their cost-effective fabrication, tunable material properties, and potential for large-area applications. This section discusses different hybrid cell types, including their material systems and performance.

2.1. Dye-Sensitized Solar Cells (DSSCs)
DSSCs rely on a sensitizing dye that absorbs light and transfers electrons to a wide bandgap semiconductor such as TiO_2. Upon light absorption, the dye injects electrons into the conduction band of the TiO_2, while the oxidized dye is regenerated by a redox electrolyte (Figure 2). Recent developments have focused on replacing liquid electrolytes with solid-state hole conductors to improve stability and performance [1]. Efficiency of DSSCs

$$\eta = \frac{P_{out}}{P_{in}} = \frac{I_{SC} \times V_{OC} \times FF}{P_{in}}$$



Fig 1: Current-voltage characteristics of a hybrid solar cell under illuminated and dark conditions.



Fig 2: Schematic of a dye-sensitized solar cell.
Source: Amrita Vishwa Vidyapeetham, Structure and Working of DSSCs

2.2. Nanoparticle-Sensitized Solar Cells

Nanoparticle-sensitized solar cells utilize quantum dots or other nanoparticles as light-absorbing sensitizers, providing a significant advantage through tunable bandgaps. The quantum confinement effect in nanoparticles enables precise control over the absorption spectrum, allowing the material to absorb light more effectively across a broader range of the solar spectrum. This tunability enhances the overall efficiency of solar cells by optimizing photon capture for different wavelengths.

Materials such as CdSe, PbS, and ZnO are commonly used for their adjustable optical properties. By varying the size and composition of the nanoparticles, their absorption peak can be shifted to align with specific portions of the solar spectrum, improving energy conversion. Figure 3 highlights the absorption spectra of different nanoparticle materials, showcasing this tunability. Nanoparticle-sensitized cells hold promise for the future of solar technology, offering a pathway toward higher efficiency and more cost-effective photovoltaic systems [5].



Fig 3: Absorption spectra of different nanoparticles used in hybrid solar cells.

- **TiO_2 nanoparticles:** Peak absorption at 350 nm.
- **ZnO nanoparticles:** Peak absorption at 380 nm.
- **CdSe quantum dots:** Tunable absorption from 450 nm to 600 nm based on particle size.

2.3. Extremely Thin Absorber (ETA) Solar Cells

Extremely Thin Absorber (ETA) solar cells utilize an ultra-thin semiconductor layer, such as $CuInS_2$, CdTe, or CuSCN, as the light-absorbing material. Unlike dye-sensitized solar cells (DSSCs), ETA cells replace traditional dye molecules with these inorganic semiconductors, which offer enhanced stability and higher absorption coefficients. The thin absorber layer allows efficient light absorption while using minimal material, reducing overall production costs and making ETA cells a potentially economical alternative to traditional solar cells.

The operation of ETA cells is conceptually similar to DSSCs, with a heterojunction formed between the thin absorber and a wide bandgap material like TiO_2. This design improves light harvesting through the increased surface area provided by the porous structure of the electrode. Moreover, the thin absorber layer minimizes charge recombination, promoting better charge separation and transport.

ETA cells have shown promising power conversion efficiencies, with performance depending on factors such as the thickness of the absorber layer and nanoparticle size. As seen in Table 1, optimizing these parameters can significantly enhance the efficiency of these devices. Continued research in this area is focused on improving material interfaces, enhancing charge mobility, and further reducing recombination losses, making ETA cells a key focus for next-generation photovoltaic technologies.

Table 1: Efficiency of ETA Solar Cells

Absorber Material	Thickness (nm)	Nanoparticle Size (nm)	Efficiency (%)
$CuInS_2$	50	10	6.5
CdTe	100	20	7.2
CuSCN	80	15	5.8

2.4. Bulk Heterojunction Hybrid Solar Cells

Bulk heterojunction (BHJ) solar cells represent a key architecture in hybrid solar cell design, blending organic polymers with inorganic nanoparticles to create a disordered yet highly functional active layer. This structure leverages the advantages of both organic and inorganic materials, with the organic polymer acting as the electron donor and the inorganic nanoparticles functioning as the electron acceptor. The intimate mixing of these two materials over nanometer scales increases the donor-acceptor interfacial area, which significantly enhances charge separation and transport efficiency.

In a typical BHJ solar cell, upon absorbing light, excitons (electron-hole pairs) are generated in the polymer. These excitons must diffuse to the donor-acceptor interface before recombination occurs. Due to the large interface created by the blending of the two materials, exciton dissociation into free charges (electrons and holes) becomes more efficient. Once separated, electrons are transported through the inorganic nanoparticles, while holes move through the polymer matrix, both migrating toward their respective electrodes. This process minimizes the energy losses typically observed in planar heterojunction solar cells, where the limited interface can constrain exciton dissociation.

The nanoparticles used in BHJ solar cells, such as CdSe, ZnO, and TiO_2, are chosen for their high electron mobility, which enhances charge extraction. Nanoparticles also offer the advantage of tunable bandgaps through quantum confinement effects, allowing the absorption spectrum to be adjusted to match the solar spectrum more closely. This is critical for maximizing light absorption and, consequently, power conversion efficiency. However, achieving the right morphology in BHJ cells is crucial; too little mixing can reduce the interfacial area for charge separation, while too much mixing can lead to percolation pathways that hinder charge transport.

Figure 4 illustrates the morphology of a typical BHJ solar cell, showing nanoparticles evenly dispersed within the polymer matrix. Optimizing this morphology is one of the most significant challenges in BHJ design. Techniques such as solvent annealing, thermal treatment, and use of co-solvents have been employed to improve the phase separation and distribution of nanoparticles within the polymer. These methods help create well-defined pathways for charge carriers, thus improving charge mobility and reducing recombination.



Fig 4: Morphology of a bulk heterojunction hybrid solar cell showing the interpenetrating network of organic and inorganic phases.

- Nanoparticle size: 20 nm.
- Polymer thickness: 200 nm.
- Blend ratio (polymer): 1:1 by weight.

Despite these advantages, BHJ solar cells face challenges, particularly in terms of achieving long-term stability and high efficiency on a commercial scale. One issue is that the morphology of the active layer can degrade over time, leading to phase separation and reduced efficiency. Furthermore, while solution processing methods (such as spin coating and printing) are cost-effective and scalable, they can introduce variability in film thickness and nanoparticle distribution, which affects device performance. Researchers are actively investigating methods to improve the robustness of the active layer and to standardize large-scale fabrication techniques.

Recent advancements in BHJ solar cells include the use of new polymer materials with higher charge mobility and more stable nanomaterials. Hybrid BHJ architectures are also being explored, where multiple types of nanoparticles are incorporated to create a multi-bandgap structure, allowing for the absorption of a broader range of light. These innovations are pushing the efficiency of BHJ solar cells closer to that of traditional silicon-based technologies, making them a promising candidate for future solar energy applications.

3. Recent Advances in Material Synthesis

Material synthesis plays a critical role in the performance of hybrid solar cells. Recent advancements include the development of high-quality inorganic nanoparticles with controlled size and shape, and the introduction of organic molecules tailored for better charge transport.

3.1. Nanoparticle Synthesis

Nanoparticle synthesis plays a crucial role in enhancing the performance of hybrid solar cells by enabling precise control over the optical and electronic properties of inorganic materials. Two widely employed techniques for synthesizing nanoparticles are colloidal synthesis and chemical vapor deposition (CVD). Each method offers unique advantages in terms of particle size control, scalability, and material purity.

Colloidal Synthesis is one of the most versatile and widely used methods for producing nanoparticles in solution. It allows for precise control over particle size, shape, and surface chemistry by adjusting reaction conditions such as temperature, precursor concentration, and reaction time. This is particularly important for materials like cadmium selenide (CdSe) quantum dots, where altering the particle size can shift the absorption spectrum from the visible to the near-infrared region, allowing the material to capture a broader range of the solar spectrum (400 nm to 700 nm) (see Figure 5). This tunability is essential for optimizing light absorption in hybrid solar cells, as it enables the design of materials that can efficiently convert sunlight into electricity. Moreover, colloidal synthesis allows for easy surface functionalization, improving nanoparticle compatibility with organic polymers in bulk heterojunction architectures.

Chemical Vapor Deposition (CVD) is another powerful technique for producing high-quality inorganic nanoparticles with excellent uniformity and crystallinity. In CVD, gaseous precursors are used to deposit thin films or nanoparticles onto a substrate, allowing for precise control over the material's composition and structure. Nanoparticles synthesized using CVD typically exhibit improved charge carrier mobility, higher stability, and fewer defects compared to colloidally synthesized particles. These properties are especially advantageous for solar cell applications, where efficient charge transport and long-term stability are critical.

In recent years, hybrid approaches combining colloidal synthesis and CVD have been explored to achieve both the scalability of colloidal techniques and the high performance associated with CVD-synthesized nanoparticles. These advancements in nanoparticle synthesis are key to developing next-generation hybrid solar cells with improved efficiency and durability.



Fig 5: Absorption spectra of CdSe quantum dots with different sizes, demonstrating tunable optical properties.

4. Performance Metrics and Commercial Viability

Hybrid solar cells are evaluated based on their efficiency, scalability, and cost-effectiveness. While traditional silicon cells still outperform in terms of efficiency, hybrid solar cells offer advantages in terms of flexibility, lightweight design, and low-cost fabrication processes.

4.1. Efficiency Trends

In the past decade, the efficiency of hybrid solar cells has seen consistent improvement. Dye-sensitized solar cells

(DSSCs) have achieved power conversion efficiencies as high as 11%, while other hybrid cell types, including nanoparticle-sensitized and bulk heterojunction cells, have also demonstrated notable gains. Figure 6 illustrates the efficiency trends over time, highlighting the steady progress made in different hybrid solar cell technologies, based on performance data [6]. Continued advancements in material engineering and device architecture are expected to push these efficiencies even higher in the coming years.



Fig 6: Efficiency trends of hybrid solar cells from 2010 to 2024 for DSSCs, nanoparticle-sensitized cells, and ETA cells.

4.2. Scalability and Commercial Prospects

Scalability is a critical hurdle for the commercial viability of hybrid solar cells. While these cells offer several advantages, including low-cost materials and flexible fabrication methods, transitioning from small-scale laboratory prototypes to large-scale production poses significant challenges. One of the primary concerns is maintaining the efficiency and performance of hybrid solar cells when scaling up to large-area devices. In small-scale research settings, precise control over material deposition, layer uniformity, and nanoparticle dispersion is feasible. However, when expanding to larger areas, issues such as inconsistent film thickness, poor nanoparticle distribution, and defects in the organic-inorganic interfaces can lead to significant efficiency losses.

Another challenge lies in the integration of nanoparticles within the hybrid structure. For optimal performance, nanoparticles need to be uniformly distributed throughout the active layer, ensuring efficient charge transport and minimal recombination losses. However, achieving this level of control on a large scale is complex and requires advanced manufacturing techniques. Methods such as roll-to-roll printing, spin-coating, or vapor deposition are being explored, but each presents its own set of challenges in terms of cost, speed, and quality control.

In addition, hybrid solar cells need to demonstrate long-term operational stability and durability for widespread commercial adoption. Scaling up production processes may exacerbate the already present issues of degradation due to environmental factors, such as moisture and UV exposure, further limiting their lifespan. Despite these challenges, hybrid solar cells hold promise for reducing the overall cost of solar energy. Table 2 outlines a cost comparison between hybrid solar cells and conventional silicon-based technologies, showing the potential economic advantage of hybrid systems. If efficiency and scalability issues can be addressed, hybrid solar cells could offer a more affordable alternative, particularly in applications requiring lightweight or flexible materials, such as in portable electronics and building-integrated photovoltaics.

Table 2: Cost Analysis of Solar Technologies (USD per Watt)

Technology	Material Cost	Fabrication Cost	Total Cost
Silicon-based Solar Cells	0.5	1	1.5
DSSCs	0.3	0.8	1.1
Nanoparticle-Sensitized Cells	0.25	0.7	0.95

5. Conclusion and Future Outlook

Hybrid solar cells represent a significant advancement in photovoltaic technology by combining the advantages of both organic and inorganic materials. Their potential for low-cost fabrication, tunability of optical properties, and flexibility makes them an attractive alternative to traditional silicon-based solar cells. In particular, their ability to use solution-based manufacturing techniques opens the possibility for mass production, thereby reducing overall costs. Hybrid cells, such as dye-sensitized solar cells (DSSCs), nanoparticle-sensitized cells, and bulk heterojunction (BHJ) cells, demonstrate promise in achieving reasonable power conversion efficiencies while leveraging inexpensive materials and simpler processing methods.

However, despite these advantages, hybrid solar cells still face several challenges that must be addressed before they can compete with conventional photovoltaic technologies. One of the most pressing issues is long-term stability. Organic materials, which are a critical component in many hybrid solar cells, are prone to degradation when exposed to environmental factors such as moisture, oxygen, and UV radiation. This degradation significantly reduces the operational lifetime of these devices, making them less attractive for large-scale applications. To overcome this, future research must focus on improving the durability of organic materials through better encapsulation techniques and the development of more stable molecules and polymers.

Another major challenge is scaling up production while maintaining efficiency. Laboratory-scale devices often perform well under controlled conditions, but when produced on a larger scale, issues such as uniformity in material deposition and interface quality arise. The development of scalable fabrication techniques that ensure consistent performance across large-area devices is essential for hybrid solar cells to become commercially viable.

Optimizing material interfaces between organic and inorganic layers is another critical area of research. Improving the charge carrier mobility and reducing recombination losses at the interface are key to enhancing overall device efficiency. Innovations in interface engineering, such as surface passivation and the use of advanced nanomaterials, will play a crucial role in overcoming these bottlenecks.

Finally, developing new nanomaterials with enhanced optical and electronic properties will push hybrid solar cells closer to their theoretical efficiency limits. Continued research into quantum dots, perovskites, and other emerging materials will expand the range of hybrid devices and improve their performance. With ongoing advancements, hybrid solar cells hold the potential to play a major role in the future of renewable energy.

6. Conflict of Interest
The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

7. References
1. Güneş S, Sariciftci NS. Hybrid solar cells. Inorganica Chim Acta. 2008;361(3):581-588. DOI: 10.1016/j.ica.2007.06.042.
2. Huynh W, Dittmer J, Alivisatos AP. Hybrid nanorod-polymer solar cells. Science. 2002;295:2425-2427.
3. Nanu M, Schoonman J, Goossens A. $TiO_2/CuInS_2$ extremely thin absorber solar cells. Adv Funct Mater. 2005;15:95-100.
4. Beek WJE, Wienk MM, Janssen RAJ. Efficient hybrid solar cells from zinc oxide nanoparticles and a conjugated polymer. Adv Mater. 2004;16:1009-1013.
5. Ramani R, Alam S, Comparative A. Influence of alkyl thiols on the structural transformations in P3HT/PCBM and P3OT/PCBM blends. Polymer. 2013;54(25):6785-6792. DOI: 10.1016/j.polymer.2013.09.028.
6. Dye-sensitized solar cell. Wikipedia. Available from: https://en.wikipedia.org/wiki/Dye-sensitized_solar_cell. [Accessed Oct 2024].
7. Dye Sensitized Solar Cells: Structure and Working. Amrita Vishwa Vidyapeetham. Available from: https://www.amrita.edu/news/dye-sensitized-solar-cells-structure-and-working. [Accessed Oct 2024].
8. Efficient P3HT bulk heterojunction organic solar cells; effect of post deposition thermal treatment. J Mater Sci Mater Electron. 2013. DOI: 10.1007/s10854-013-1401-0.
9. Morphology of polymer/fullerene bulk heterojunction solar cells. J Mater Chem. Available from: https://pubs.rsc.org/en/content/articlelanding/2005/jm/b510618b. [Accessed Oct 2024].